



PEEK

Unfilled, Extruded PolyEtherEtherKetone

Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	0.0473 lb/in ³	ASTM D792
Water Absorption	0.1 %	0.1 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	0.5 %	0.5 %	Immersion; ASTM D570(2)
Mechanical Properties			
Hardness, Rockwell M	100	100	ASTM D785
Hardness, Rockwell R	126	126	ASTM D785
Hardness, Shore D	85	85	ASTM D2240
Tensile Strength, Ultimate	110 MPa	16000 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Tensile Modulus	4.34 GPa	630 ksi	ASTM D638
Flexural Modulus	4.14 GPa	600 ksi	ASTM D790
Flexural Yield Strength	172 MPa	25000 psi	ASTM D790
Compressive Strength	138 MPa	20000 psi	10% Def.; ASTM D695
Compressive Modulus	3.45 GPa	500 ksi	ASTM D695
Shear Strength	55.2 MPa	8000 psi	ASTM D732
Coefficient of Friction	0.4	0.4	Dry vs. Steel; QTM55007
K (wear) Factor	755 x 10 ⁻⁸ mm ³ /N-M	375 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.298 MPa-m/sec	8500 psi-ft/min	4:1 safety factor; QTM 55007
Izod Impact, Notched	0.534 J/cm	1 ft-lb/in	ASTM D256 Type A
Electrical Properties			
Surface Resistivity per Square	Min 1e+013 ohm	Min 1e+013 ohm	EOS/ESD S11.11
Dielectric Constant	3.3	3.3	1MHz; ASTM D150
Dielectric Strength	18.9 kV/mm	480 V/mil	Short Term; ASTM D149
Dissipation Factor	0.003	0.003	1MHz; ASTM D150
Thermal Properties			
CTE, linear 68°F	46.8 µm/m-°C	26 µin/in-°F	(-40°F to 300°F); ASTM E831
Thermal Conductivity	0.252 W/m-K	1.75 BTU-in/hr-ft ² -°F	ASTM F433
Melting Point	340 °C	644 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	249 °C	480 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	160 °C	320 °F	ASTM D648
Flammability, UL94 (Estimated Rating)	V-0	V-0	1/8 inch